

# MJL Industrial, Inc.

## Aluminum Trihydrate (Aluminum Hydroxide)

### MJ – HF135

SiO <sub>2</sub> :	0.04%	maximum
Fe <sub>2</sub> O <sub>3</sub> :	0.02%	maximum
Na <sub>2</sub> O:	0.3%	maximum
Moisture:	0.3%	maximum
L.O.I.:	34.5 ± 0.5	
Whiteness:	98	minimum
Average Particle Size:	6 - 11 μ	
Pass through 320 mesh:	97%	minimum
Standard packaging:	25 KG net Plastic Bag.	

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

---

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;  
E-mail: [webmaster@mjlindustrial.com](mailto:webmaster@mjlindustrial.com)

Revised: January 1, 2006