

MJL Industrial, Inc.

CALCIUM ACETATE

MJ Ca-ACT

- ♣ Catalyst for manufacturing PTA and DMT
- ♣ Catalyst for PSF, PFY, Polyester Film and PET Bottle Resin production using DMT route

Typical Properties

MJ Ca-ACT

Chemical Description	Calcium Acetate Hydrate Ca (CH ₃ COO) ₂ • H ₂ O	
Physical Appearance	Pure-white crystal	
Calcium Acetate	99.0%	Minimum
Manesium (Mg)	20 ppm	Maximum
Iron (Fe)	20 ppm	Maximum
Lead (Pb)	20 ppm	Maximum
Chlorides	50 ppm	Maximum
Sulfates	50 ppm	Maximum
Water Insoluble	0.01%	Maximum
Free Acid	0.3%	Maximum

Packaging: 15 KG or 20 KG lined plastic bag

Identification: CAS# 62-54-4

H.S. Tariff Code: 2918.29.04

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;
E-mail: webmaster@mjlindustrial.com

Revised: January 1, 2006