

# MJL Industrial, Inc.

## Magnesium Hydroxide

### MJ Mg-5A Grade

Appearance:	White free flowing powder	
Assay Mg(OH) <sub>2</sub>	99+%	
CaO	0.05%	Maximum
Chloride	0.05%	Maximum
Volatile	0.5%	Maximum
Average Particle Size	0.7 – 2 u	
Refractive Index	1.56 ~ 1.58	

Excellent Water & Acid Resistance; Recommended for Polyolefin Applications.

Standard packaging: 20 KG net PE-lined woven bags.

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

---

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;  
E-mail: [webmaster@mjlindustrial.com](mailto:webmaster@mjlindustrial.com)

Revised: January 1, 2006