

MJL Industrial, Inc.

Melamine PyroPhosphate

MJ-MPP

Appearance:	Free flowing white powder
P:	13.5 % minimum
N:	25 % minimum
pH:	5 - 6
Soluble in water:	0.15 % maximum
Pass through 30 um mesh:	95 % minimum
Standard packaging:	20 KG PE lined woven bag.

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;
E-mail: webmaster@mjlindustrial.com

Revised: January 1, 2006