

MJL Industrial, Inc.

ANTIMONY TRISGLYCOLATE CATALYST

MJ PET-ATG

- ♣ High Performance Polycondensation Catalyst for PET and Polyester
- ♣ Recommended for both **PTA** and **DMT** processes
- ♣ Suitable for both **Continuous** and **Batch** processes
- ♣ Reduced waste discharge treatment cost

Typical Properties

MJ PET-ATG

Chemical Description	Antimony Tris(Ethylene Glycoxide)
Physical Appearance	Off-white Crystalline Powder
Antimony Content	57.5% ± 1%
Arsenic (As)	20 ppm Maximum
Lead (Pb)	20 ppm Maximum
Iron (Fe)	15 ppm Maximum
Copper (Cu)	10 ppm Maximum
Nickel (Ni)	10 ppm Maximum
Chlorides	10 ppm Maximum
Sulfates	10 ppm Maximum
Solubility	1.6% in dry MEG @ 25°C

Packaging: **15 KG HDPE pail; or, customer's option.**

Identification: **CAS# 29736-75-2**

UN# not regulated

H.S. Tariff Code: **8110.00.00**

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;

E-mail: webmaster@mjlindustrial.com

Revised: January 1, 2006