

MJL Industrial, Inc.

Alkyl Diphenyl Phosphate Ester Flame Retardant Plasticizer

MJ-ADPE

Appearance	Clear, oily liquid
Specific Gravity @25°C	1.028 – 1.044
Water Content, Karl Fischer	0.1% maximum
Acidity (meq/100 gm)	0.2 maximum
Color (Pt/Co Scale)	200 maximum
Viscosity, Centistokes @25°C	25
Water Solubility @25°C	< 0.2 mg/L
Flash Point	445°F

Applications: **Low smoke, flame retardant plasticizer** for (a) PVC Riser/Plenum Wire & Cable applications; (b) PVC Alloys for molded parts in Electrical and Automotive applications.

Standard packaging: 200 KG net plastic drum

The above table gives typical analysis based on historical production performance. MJL does not make any express or implied warranty that future production will demonstrate or continue to possess these typical analysis.

405 Uxbridge Way, Hockessin, DE 19707, USA; Tel: +1 (302) 234-0898; Fax: +1 (302) 234-4167;

E-mail: webmaster@mjlindustrial.com

Revised: January 1, 2006